



IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Applicant : Jan Eirik Ellingsen et al. Art Unit : 1763
Serial No. : 09/602,528 Examiner : Roberts P. Culbert
Filed : June 23, 2000
Title : METALLIC IMPLANT AND PROCESS FOR TREATING A METALLIC IMPLANT

MAIL STOP ISSUE FEE

Commissioner for Patents
P.O. Box 1450
Alexandria, VA 22313-1450

TRANSMITTAL OF PRIORITY DOCUMENT UNDER 35 USC §119

Further to the Letter Accompanying Reply to Action of June 22, 2005 filed December 13, 2005, attached are certified copies of the priority documents. Applicant hereby confirms his claim of priority under 35 USC §119 from the following applications:

·Sweden Application No. 9304209-1, filed December 20, 1993

·Sweden Application No. 9401928-8, filed June 3, 1994

A certified copy of each application from which priority is claimed is submitted herewith.

Please apply any charges or credits to Deposit Account No. 06-1050, referencing Attorney Docket Number .

Respectfully submitted,

Date: _____

3/28/06

Denis G. Maloney
Reg. No. 29,670

Fish & Richardson P.C.
225 Franklin Street
Boston, MA 02110
Telephone: (617) 542-5070
Facsimile: (617) 542-8906

21296482.doc

CERTIFICATE OF MAILING BY FIRST CLASS MAIL

I hereby certify under 37 CFR §1.8(a) that this correspondence is being deposited with the United States Postal Service as first class mail with sufficient postage on the date indicated below and is addressed to the Commissioner for Patents, P.O. Box 1450, Alexandria, VA 22313-1450.

Date of Deposit

March 28, 2006

Signature

M. Krugger

Typed or Printed Name of Person Signing Certificate

Melissa Krugger

PRV

PATENT- OCH REGISTRERINGSVERKET
Patentavdelningen

Intyg Certificate

Härmed intygas att bifogade kopior överensstämmer med de handlingar som ursprungligen ingivits till Patent- och registreringsverket i nedannämnda ansökan.

Ansökan ingavs ursprungligen på engelska.

This is to certify that the annexed is a true copy of the documents as originally filed with the Patent- and Registration Office in connection with the following patent application.

The application was originally filed in English.

(71) Sökande Astra AB, Södertälje SE
Applicant (s)

(21) Patentansökningsnummer 9304209-1
Patent application number

(86) Ingivningsdatum 1993-12-20
Date of filing

Stockholm, 2005-12-14

För Patent- och registreringsverket
For the Patent- and Registration Office



Hjärdís Segerlund

Avgift

Fee 170:-

NEW PROCESS FOR TREATING A METALLIC SURGICAL
IMPLANT

1993-12-16

5 This invention relates to a process for treating a metallic surgical implant,
particularly an implant made of titanium or a titanium alloy.

Background of the Invention

10 Titanium and titanium alloys are frequently used as implant materials in dental and
orthopedic surgery because of their good compatibility with bone tissue and their
tendency to form a firm attachment directly with bone tissue. The interaction
between bone tissue and metal, leading to such firm attachment, was coined
"osseointegration" by Brånemark and co-workers, of Gothenburg, Sweden, in the
late 1970's, but the mechanics of the attachment process are not yet fully
understood.

15 The standard surgical technique for fixing a surgical implant involves a two-stage
process. In the first stage the soft tissue covering the bone tissue is opened and a
base part of the implant is placed in the bone tissue. The soft tissue is closed and
the implant left to osseointegrate for a comparatively long period of time. In the
20 second stage the soft tissue is re-opened and the load-bearing parts of the implant
are attached to the base part. A two-stage technique such as this has some
disadvantages, since the long period needed for osseointegration is very
uncomfortable for the patient. Furthermore, in orthopaedics it is preferable to have
a one-stage operation since a joint, for example the hip joint, should not be
25 operated on twice if this can be avoided. One prerequisite of a one-stage operation
is that the time needed to obtain sufficient strength at the bone tissue -implant
interface, is short. In addition, there may be problems in obtaining a full
osseointegration in those cases where the quality of the bone is poor or the
available space is limited, for example in the upper jaw or in the posterior parts of
30 the lower jaw above the nerve. In these places it would therefore be desirable to

stimulate the regeneration of the bone tissue around the implant.

5 There are to date several methods for treating implants made of titanium in order to obtain a better attachment of the implant. Some of these involve altering the topography of the implant, for example by creating relatively large irregularities on the implant surface in order to obtain a better mechanical retention and to increase the area of attachment, by for example plasma spraying, blasting or etching. Although the retention may be improved, the time necessary for the osseointegration process may be longer since the bone tissue would have to grow into the irregularities in the surface.

10 Other methods involve altering of the chemical properties of the implant surface. For example one such method involves the application of a layer of ceramic material such as hydroxyapatite to the implant surface, inter alia in order to stimulate the regeneration of the bone tissue. Ceramic coatings however may be brittle and may flake or break off from the implant surface, which may in turn lead to the ultimate failure of the implant.

20 US Patent No. 4,330,891 could perhaps be said to combine each of the above, in that the provision of an element with a micro-pitted surface which micro-pits are within a certain diameter range, is said to effect improved properties as regards acceptance of the carrier element, and primarily improved durability of the healthy ingrowth of the element due to its biological quality.

25 The Invention

It is the object of the present invention to provide a metallic surgical implant having improved strength of connection with bone. This object is achieved by treating a metallic surgical implant with an aqueous solution of hydrofluoric acid (HF) according to the present invention.

30

According to the present invention, therefore, there is provided a process for treating a metallic surgical implant prior to implantation, comprising treating the said implant with an aqueous solution of HF ("the treatment solution"), which solution is of pH 1.6 to pH 6.

5

Preferably, the aqueous solution is of pH 1.6 to pH 3.

The present invention is particularly of interest in the treatment of titanium or titanium alloy, such as Ti/Al alloy, implants, but may also be employed for the treatment of other metallic implants such as those of zirconium and tantalum, and coated metallic implants such as hydroxyapatite-coated titanium.

10

The treatment solution preferably contains HF in a concentration of 0.001% to 3.0%, such as 0.01% to 3.0% or 0.1% to 2.0%. Most preferably the concentration of HF is 0.2%.

15

Treatment of the metallic surgical implant may be carried out in any suitable manner, for example by immersing the implant in the treatment solution for a period of time and with or without agitation. Varying temperatures may be employed; parameters such as temperature and time may be selected according to the concentration of the treatment solution and the other process parameters. In most cases, for treatments at room temperature, treatment should be carried out for at least ten seconds such as from ten seconds to six hours; in the case of a 0.2% solution, treatment at room temperature for around two minutes is preferable.

20

Treatment is conveniently carried out at standard pressure, but elevated pressures may be used where desired. Preferably, treatment is carried out at standard pressure and temperature.

25

The treatment solution of the present invention may be simply prepared, by diluting concentrated HF with distilled water.

30

Prior to treatment, the implant material may be cleaned by standard techniques such as are well known in the art.

5 After treatment, the implant material may be washed in distilled water and kept under sterile conditions.

10 In titanium implants treated according to the present invention, a force up to sixteen times greater than that needed to displace untreated implants, was required in order to displace the said implants from bone. In addition, the results obtained showed a good correlation between animals, indicating less deviation in the effect of treatment of the implants from animal to animal when compared with the widely varying results obtained from untreated implants. The implants tested were conical in shape such that mechanical and frictional influences were minimised. It is believed that the improved properties found in implants treated according to the present invention are the result of improved biocompatibility and osseointegration resultant from the treatment process. While we do not wish to be limited to the expression of theories herein, the improved biocompatibility is thought to be due, at least in part, to fluoride being retained on the surface of the treated implant.

20 The invention will now be illustrated by Example.

Examples

Comparative Example

25 Seven surgical implants, of commercially pure (c.p.) titanium, 5 mm in length and generally conical in shape having a diameter at one end of 3 mm and at the other end 2 mm, were prepared by machining using a "Maximat super 11" (TM) turning lathe. Therefore the area of the conical sides of the implant, i.e. the part of the implant to be located in the bone, is 39 mm^2 .

30 Each implant was cleaned according to a well-known cleaning procedure involving

the following steps:

1. Treatment with trichloroethylene with ultrasonic treatment, for 15 minutes.
- 5 2. Rinsing in absolute ethanol, for 10 seconds.
3. Three successive treatments with ethanol with ultrasonic treatment, each for 10 minutes.

Each cleaned implant was sterile packaged in a Mediplast (TM) sterile envelope, and autoclaved in a Citomat 162 (TM) (LIC Company) autoclave, at 120 C for 30 minutes.

Example 1

A HF bath was prepared simply by diluting concentrated HF with distilled water, to give a 0.2% solution. The pH of the bath was 2.1.

15

Seven implants, prepared, cleaned, sterile packaged and autoclaved exactly as in the Comparative Example above, were removed from their sterile packages, placed in the HF treatment bath and left there for two minutes. Thereafter each was washed three times in a bath of distilled water, for periods of 30 seconds each wash. After being allowed to dry at room temperature, each implant was transferred to a Mediplast (TM) sterile envelope to await surgical implantation.

Implant study

Chinchilla rabbits were used as test animals. The rabbits were randomly distributed regarding sex, but all had a weight of 2.5 kg at the start of the study. Each animal was sedated by injection using a combination of fluanzozonium 1.0 mg/kg and fentanylum 0.02 mg/kg (Hypnorm, Janssen Pharmaceuticals, Belgien) and locally anesthetised with xylocaine/adrenaline (AB Astra). Two cavities were drilled in each rabbit's right ulna, using standardised bores designed to provide cavities into which the conical implants would exactly fit. Implants according to

30

the Comparative Example or Example 1 were placed in the cavities of each rabbit, using titanium tweezers so as to avoid the influence of other metals, and left for sixty days.

- 5 At the end of sixty days the rabbits were sacrificed by injection with pentobarbital sodium, and the ulna's removed and placed in sterile physiological saline to await a "push-out" test the same day.

- 10 An Instron model 1121 tensile testing machine (Instron, U.K.) inter alia comprising a support jig and a ram adjusted for a load range of 0 - 200 N, was employed to measure the force needed to separate each implant from bone. Milling tracks, to fit the support jig, were made in the specimen to be tested, in the bone surrounding the larger end of the implant, and the specimen was placed on the support jig. The ram was lowered at a speed of 1 mm/min., and the force required to separate the
15 implant from the bone was recorded.

This recorded force gives a direct assessment of the strength of connection of the implant and bone, the higher the required force the stronger the connection.

- 20 The results are recorded in Table 1.

25

30

Table 1

Recorded force (N)

	Implants according to the Comparative Examples		Implants according to Example 1	
5	1	18.1	1	84.1
	2	59.2	2	96.0
	3	44.7	3	64.2
	4	39.2	4	62.7
10	5	59.5	5	64.9
	6	6.0	6	89.5
	7	8.5	7	89.5
	mean 33.6		mean 78.7	

- 15 The much greater strength of bone connection with implants treated in accordance with the present invention is apparant from the above.

Histological examination demonstrated that the implants according to Example 1 were surrounded even in the ulna's spongiosa by a thick layer of newly formed bone which was in close contact with the implants. In contrast the untreated implants, i.e. those according to the Comparative Examples, were only partly covered, by a thin bone layer, in the spongiosal area.

CLAIMS

1. A process for treating a metallic surgical implant prior to implantation, comprising treating said implant with an aqueous solution of HF,
5 which solution is of pH 1.6 to pH 6.
2. A process according to claim 1, wherein the aqueous solution is of pH 1.6 to pH 3.
- 10 3. A process according to claim 1 or claim 2, wherein the metallic surgical implant comprises titanium or a titanium alloy.
4. A process according to claim 1, 2 or 3, wherein the concentration of HF is in the range 0.001% to 3.0%.
15
5. A process according to claim 4, wherein the concentration of HF is in the range 0.01% to 3.0%.
6. A process according to claim 4, wherein the concentration of HF is in
20 the range 0.1% to 0.2%.
7. A process according to claim 4, 5 or 6, wherein the concentration of HF is approximately 0.2%.

8. A process according to any of claims 1 to 3 and 7, wherein the pH of the solution is approximately 2.1.


9. A process according to any preceeding claim, wherein said treatment
5 comprises immersing the implant in the aqueous solution at room temperature for a period of at least ten seconds.

10. A process according to any of claims 1 to 3 and 8 to 9, wherein said treatment comprises immersing the implant in the aqueous solution at room
10 temperature for ten seconds to six hours.

11. A process according to any of claims 1 to 3 and 8 to 10, wherein said treatment comprises immersing the implant in the aqueous solution at room temperature for a period of approximately 2 minutes.

15

12. A metallic surgical implant treated by the process of any of claims 1 to 11.



PAU 93.12.20 M
10

ABSTRACT OF THE INVENTION

**Metallic surgical implant materials having improved strength of connection with
bone are produced when the implants are treated prior to implantation with
5 aqueous HF.**

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25